

## **Confidential Report**

Our Ref: 25/09657C/06/19



Notified Body for PPE Directive, Construction Products Regulation & Marine Equipment Directive I.D. No. 0338 & 0339



Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 03 July 2019

Our Ref: 25/09657C/06/19

Your Ref:

Page: 1 of 8

Client:	Jacaranda Carpets Limited		
	1 Cockerel Rise		

Magnetic Park Desborough Northamptonshire

**NN14 2WE** 

Job Title: Fire Test on One Sample of Carpet

Client's Order No: ---

Date of Receipt: 12 June 2019

Description of Sample(s): One sample of hand woven carpet, referenced; KASIA, 100% Tencel

Work Requested: We were asked to make the following test(s):

BS EN 13501-1

Note: This report relates only to the samples submitted and as described in the report.

- \* subcontracted test, UKAS accredited
- \*\* subcontracted test, EN ISO/IEC 17025 accredited
- \*\*\* not UKAS accredited





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 03 July 2019

Our Ref: 25/09657C/06/19

Your Ref:

Page: 2 of 8

**Client: Jacaranda Carpets Limited** 

# FIRE TESTS ACCORDING TO BS EN ISO 11925-2:2010 Reaction to fire tests for building products – Part 2: Ignitability when subjected to direct impingement of flame

Date of Test: 01/07/2019

#### **Conditioning**

Test specimens and filter paper conditioned as described in BS EN 13238:2010.

#### **Procedure**

The sample was tested in accordance with BS EN ISO 11925-2:2010.

Three specimens from each direction were tested in accordance with the above standard. Specified filter paper was placed beneath the specimen holder and replaced between tests.

The specimens were mounted vertically in the specimen holder so that one end and both sides were enclosed with the exposed end 30mm from the end of the frame. The burner was inclined at an angle of 45°. The flame height was set at 20 mm with the flame impinging on the specimen for 15 seconds on the centre line, 40 mm above the bottom edge.

A marker was placed 150 mm above the upper end of the burner and the time recorded when the flame tip reached the marker, if applicable. The following parameters were also recorded:-

- 1. If ignition occurs
- 2. Presence of flaming debris, if applicable
- 3. Ignition of the filter paper, if applicable

1066

#### **Duration of test**

For a flame application time of 15 seconds, the total test duration is 20 seconds after application of the flame.





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

03 July 2019

25/09657C/06/19

Our Ref: Your Ref:

Date:

Page: 3 of 8

**Client: Jacaranda Carpets Limited** 

#### **Classification Criteria**

The samples were classified according to BS EN 13501-1:2007+A1:2009 Fire classification of Construction Products and Building Elements: Part 1 – Classification using Test Data from Reaction to Fire Tests, Table 1 – Classes of reaction to fire performance for construction products excluding floorings.

Flaming Classification		
Classification Criteria (mean values)		
E <sub>FL</sub>	Fs ≤ 150mm within 20 seconds	
F <sub>FL</sub>	None ( No performance determined)	

Flaming droplets / particles classification		
Classification Criteria		
No classification	Pass	
d2	Fail (Ignition of paper)	

#### **Results**

Specimen			Tip of flame reaches 150mm		Flaming droplets	
		Ignition (Yes or No)	Yes or No	Time taken (s)	Yes or No	Ignition of Filter paper (Yes or No)
	1	Yes	No	N/A	No	No
Direction	2	Yes	No	N/A	No	No
	3	Yes	No	N/A	No	No
Across	1	Yes	No	N/A	No	No
Machine 2	2	Yes	No	N/A	No	No
	3	Yes	No	N/A	No	No





Telephone: +44 (0) 113 259 1999

Email: <a href="mailto:info@bttg.co.uk">info@bttg.co.uk</a>
Website: <a href="mailto:www.bttg.co.uk">www.bttg.co.uk</a>

Date: 03 July 2019

Our Ref: 25/09657C/06/19

Your Ref:

Page: 4 of 8

Client: Jacaranda Carpets Limited

#### FIRE TESTS ACCORDING TO BS EN ISO 9239-1:2010 Indicative

Reaction to fire tests for Floorings - Part 1: Determination of the burning behaviour using a radiant heat source (ISO 9239-1:2010)

Date of Test: 01/08/2019

#### **Conditioning**

The specimen was conditioned in accordance with BS EN 13238:2010. The substrate used was a fibre cement board (ISO 390) with a thickness of  $(6\pm1)$ mm and a density of  $(1,800\pm200)$  Kg/m<sup>3</sup> representing the standard substrate of Class A1<sub>fl</sub> or A2<sub>fl</sub>.

#### **Procedure**

The test was carried out in accordance with BS EN ISO 9239-1. The sponsor sampled and cut the specimen to the dimensions stated.

The specimen was individually placed in the combustion chamber and allowed to preheat for two minutes under a radiant panel, which gives an imposed radiant flux ranging from approximately 11 kW/m² to 1 kW/m² along the specimen.

The pilot flame used was the line burner as described and was applied to the surface of the specimen for 10 minutes and then removed.

The flame front was measured at the end of the test or at 30 minutes if applicable.

Test termination was considered to be when the flame front self extinguished or at 30 minutes, which ever is the sooner.

The heat flux from the panel incident on the specimen when self extinguished or at 30 minutes (critical heat flux CHF or HF-30) was calculated from a prior calibration.





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 03 July 2019

Our Ref: 25/09657C/06/19

Your Ref:

Page: 5 of 8

**Client: Jacaranda Carpets Limited** 

#### **Classification Criteria**

The sample was classified according to BS EN 13501-1:2007+A1:2009: Fire classification of Construction Products and Building Elements: Part 1: Classification using Test Data from Reaction to Fire Tests.

For Floorings including their surface coverings the classes are:

Classification	Classification Criteria (mean values) (kW/m²)
B <sub>fl</sub>	8.0
C <sub>fl</sub>	4.5
D <sub>fl</sub>	3.0
	Smoke Production % x min
s1	≤ 750
s2	Not s1

When tested to BS EN ISO 11925-2:2010 the sample has to have a flame spread (Fs) of: Fs  $\leq$  150mm within 20 seconds (Class Efl)

#### **Results**

The test results relate to the behaviour of the test specimen of a material under the particular conditions of test; they are not intended to be the sole criterion for assessing the full potential fire hazard of the materials in use.





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 03 July 2019

Our Ref: 25/09657C/06/19

Your Ref:

Page: 6 of 8

**Client: Jacaranda Carpets Limited** 

#### **Results (continued)**

Direction of	Smoke Obscuration		<u>Maximum</u>	Critical Heat	<b>Duration of</b>
<u>specimen</u>	Max %	<u>% x min</u>	Flame front	Flux (kW/m²)	Flaming (sec)
			<u>(mm)</u>		
Machine	17	137	980	1.4	1800
iviacillie	1/	13/	300	1.4	1000

<u>Distance</u> <u>Burnt (mm)</u>	Time for each specimen to burn (s)
50	140
100	148
150	158
200	180
250	198
300	221
350	255
400	300
450	330
500	420
550	510
600	600
650	660
700	740
750	880
800	990
850	1200
900	1500
950	1690

#### Note

Only one specimen was tested. Results of 3 specimens in the same direction are used to determine an absolute class.

The specimen of floor covering was tested loose laid onto a 6mm fibre cement board as defined in BS EN 13238:2010.







Wira House, West Park Ring Road, Leeds, LS16 6QL, UK. Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk

Website: www.bttg.co.uk

Date: 03 July 2019

Our Ref: 25/09657C/06/19

Your Ref:

Page: 7 of 8

**Client: Jacaranda Carpets Limited** 

#### **Comments**

In our opinion, based on the tests carried out on the sample supplied;

- a) the results of the BS EN ISO 11925-2:2010 test indicate the sample meets the requirements of a Class E<sub>FL</sub>. It should be noted that this is only class that can be achieved when tested to this method alone.
- b) the results of the BS EN ISO 9239-1:2010 test indicate the sample is unclassifiable when tested to this method alone. Therefore, the test was terminated after one specimen.

#### Conclusion

In our opinion, the results indicate that the sample when classified to BS EN 13501-1:2007+A1:2009 meets an overall classification of: Class  $E_{\rm fl}$ .

Reported by:

B Marsden (Mrs), Senior Fire Technician

Countersigned by:

P Doherty, Executive Manager

Enquiries concerning this report should be addressed to Customer Services...





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 03 July 2019

Our Ref: 25/09657C/06/19

Your Ref:

Page: 8 of 8

**Client: Jacaranda Carpets Limited** 

### **Uncertainty Budget - Annex**

The uncertainty budget for BS EN 13501-1: 2007+A1:2009 was determined as follows:-

#### Overall (BS EN ISO 9239-1)

The uncertainty varies, therefore:

At position between a Euroclass B to C  $\pm$  15% At position between a Euroclass C to D  $\pm$  15.5% At position between a Euroclass D to E  $\pm$  17.5%

